

<b>Chemical Analysis</b>		
Silica	(SiO <sub>2</sub> )	64.20%
Alumina	(Al <sub>2</sub> O <sub>3</sub> )	20.24%
Iron Oxide	(Fe <sub>2</sub> O <sub>3</sub> )	4.86%
Titanium Oxide	(TiO <sub>2</sub> )	.70%
Calcium Oxide	(CaO)	2.00%
Magnesium Oxide	(MgO)	3.62%
Alkalies		3.16%
Sulphur Trioxide	(SO <sub>3</sub> )	.69%
Loss on Ignition		.30%